



**AMES  
GOLDSMITH**  
Corp.

**DEVELOPMENT PRODUCT**

## Silver Platelet Type S3-500

### GENERAL DESCRIPTION

Medium density mono-dispersed 300-500 nm silver platelet


### APPLICATIONS

Fired and non-fired thick film paste systems for fine line printing  
Polymer thick film

### TYPICAL PROPERTIES

Physical Data:		Particle Size Distribution:	
Tap Density:	1.5-3.0 g/cm <sup>3</sup>	D10	100 nm
Surface Area:	1.0-2.5 m <sup>2</sup> /g	D50	300 nm
Loss on Drying: (1 hour @ 110°C in air)	<0.5 %	D90	700 nm
Loss on Ignition (1 hour @ 538°C in air)	<0.5 %		
		PSD determined by FSEM	

This product is also available “wet”, dispersed in a solvent of choice.



Released: 11/07

21 Roger Street, Glens Falls, NY 12801  
TEL: (518)-792-5808 FAX: (518)-792-1034  
[www.amesgoldsmith.com](http://www.amesgoldsmith.com)  
Email: [sales@amesgoldsmith.com](mailto:sales@amesgoldsmith.com)



The statements and data contained herein are considered to be accurate and have been determined by Ames Goldsmith using commonly accepted methods. Ames Goldsmith makes no warranty with respect to the information in whole or in part. The use and application of such information is at the user's own discretion and risk, without any liability on the part of Ames Goldsmith. The physical and chemical data reported is representative of our standard process. Ames Goldsmith has the expertise to modify our processes to provide a product that best suits your application.